



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification: H01M 4/88, H01M 8/10	A3	(11) International Publication Number: WO 00/45448 (43) International Publication Date: 03 August 2000 (03.08.2000)
(21) International Application Number: PCT/US00/01810 (22) International Filing Date: 24 January 2000 (24.01.2000) (30) Priority Data: 60/116,747 22 January 1999 (22.01.1999) US (60) Parent Application or Grant CALIFORNIA INSTITUTE OF TECHNOLOGY [/]; (). NARAYANAN, S., R. [/]; (). ATTL, Tony [/]; (). PRAKASH, Surya [/]; (). OLAH, George [/]; (). SMART, Marshall, C. [/]; (). NARAYANAN, S., R. [/]; (). ATTL, Tony [/]; (). PRAKASH, Surya [/]; (). OLAH, George [/]; (). SMART, Marshall, C. [/]; (). HARRIS, Scott, C. ; ().		Published
(54) Title: IMPROVED MEMBRANE ELECTRODE ASSEMBLY FOR A FUEL CELL (54) Titre: ENSEMBLE AMELIORE D'ELECTRODES A MEMBRANE CONÇU POUR PILE A COMBUSTION (57) Abstract <p>A catalyst ink for a fuel cell including a catalytic material and poly(vinylidene fluoride). The ink may be applied to a substrate to form an electrode, or bonded with other electrode layers to form a membrane electrode assembly (140).</p> (57) Abrégé <p>L'invention concerne une encre de catalyseur destinée à une pile à combustion comprenant un matériau catalytique et du poly(vinylidène fluoride). On peut appliquer l'encre sur un substrat pour former une électrode, ou la fixer sur d'autres couches d'électrodes pour constituer un ensemble d'électrodes à membrane (MEA).</p>		

BEST AVAILABLE COPY

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
3 August 2000 (03.08.2000)

PCT

(10) International Publication Number
WO 00/45448 A3

(51) International Patent Classification⁷: H01M 4/88, 8/10

(21) International Application Number: PCT/US00/01810

(22) International Filing Date: 24 January 2000 (24.01.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/116,747 22 January 1999 (22.01.1999) US

(63) Related by continuation (CON) or continuation-in-part (CIP) to earlier application:
US 60/116,747 (CIP)
Filed on 22 January 1999 (22.01.1999)

(71) Applicant (for all designated States except US): CALIFORNIA INSTITUTE OF TECHNOLOGY [US/US];
1200 East California Boulevard, Mail Code 201-85,
Pasadena, CA 91125 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): NARAYANAN, S., R. [US/US]; California Institute of Technology, Jet


Propulsion Laboratory, 4800 Oak Grove Drive, Mail Code 277-207, Pasadena, CA 91109 (US). ATTI, Tony [US/US]; California Institute of Technology, Jet Propulsion Laboratory, 4800 Oak Grove Drive, Mail Code 277-207, Pasadena, CA 91109 (US). PRAKASH, Surya [US/US]; California Institute of Technology, Jet Propulsion Laboratory, 4800 Oak Grove Drive, Mail Code 277-207, Pasadena, CA 91109 (US). OLAH, George [US/US]; University of Southern California, Loker Hydrocarbon Research Institute, 837 West 37th Street, Room 204, Los Angeles, CA 90089 (US). SMART, Marshall, C. [US/US]; California Institute of Technology, Jet Propulsion Laboratory, 4800 Oak Grove Drive, Mail Code 277-207, Pasadena, CA 91109 (US).

(74) Agent: HARRIS, Scott, C.; Fish & Richardson P.C., Suite 500, 4350 La Jolla Village Drive, San Diego, CA 92122 (US).

(81) Designated States (national): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT,

[Continued on next page]

(54) Title: IMPROVED MEMBRANE ELECTRODE ASSEMBLY FOR A FUEL CELL



WO 00/45448 A3

(57) Abstract: A catalyst ink for a fuel cell including a catalytic material and poly(vinylidene fluoride). The ink may be applied to a substrate to form an electrode, or bonded with other electrode layers to form a membrane electrode assembly (140).



RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA,
UG, US, UZ, VN, YU, ZA, ZW.

Published:

— With international search report.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(88) Date of publication of the international search report:
30 November 2000

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/01810

A. CLASSIFICATION OF SUBJECT MATTER														
IPC(7) : H01M 4/88, 8/10 US CL : 429/40, 42 According to International Patent Classification (IPC) or to both national classification and IPC														
B. FIELDS SEARCHED														
Minimum documentation searched (classification system followed by classification symbols) U.S. : 429/27, 40-43; 427/115; 502/101														
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched														
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) EAST (USPAT, DERWENT, EPO, JPO) search terms: fuel cell, catalysts, polyvinylidene fluoride, styrene, polystyrene														
C. DOCUMENTS CONSIDERED TO BE RELEVANT														
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.												
X — Y	US 5,783,325 A (CABASSO et al) 21 July 1998, col. 6, lines 22-51; col. 7, lines 64-67; col. 8, lines 1-3.	1,2,6-9,11,14,15 ----- 5,10,23												
X	US 5,677,074 A (SERPICO et al) 14 October 1997, abstract; col. 2, lines 20-47; col. 6, lines 49-53.	1-4,6-8, 11,14,17, 18												
Y	WO 98/22989 (PRAKASH et al) 28 May 1998, abstract; pages 23, 28, and 40.	12,13, 16-22, 24-26												
Y	US 5,656,386 A (SCHERER et al) 12 August 1997, col. 3, lines 27-28, lines 45-64; col. 8, lines 57-58; col. 10, lines 33-38.	13												
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.														
<table border="0"> <tr> <td>* Special categories of cited documents:</td> <td>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>"A" document defining the general state of the art which is not considered to be of particular relevance</td> <td>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>"E" earlier document published on or after the international filing date</td> <td>"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>"&" document member of the same patent family</td> </tr> <tr> <td>"O" document referring to an oral disclosure, use, exhibition or other means</td> <td></td> </tr> <tr> <td>"P" document published prior to the international filing date but later than the priority date claimed</td> <td></td> </tr> </table>			* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	"E" earlier document published on or after the international filing date	"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family	"O" document referring to an oral disclosure, use, exhibition or other means		"P" document published prior to the international filing date but later than the priority date claimed	
* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention													
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone													
"E" earlier document published on or after the international filing date	"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art													
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family													
"O" document referring to an oral disclosure, use, exhibition or other means														
"P" document published prior to the international filing date but later than the priority date claimed														
Date of the actual completion of the international search 07 JULY 2000		Date of mailing of the international search report 04 AUG 2000												
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230		Authorized officer SUSY TSANG Telephone No. (703) 308-0666 DEBORAH THOMAS PARALEGAL SPECIALIST												

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/01810

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4,272,353 A (LAWRANCE et al) 9 June 1981, abstract.	16
Y	US 5,186,877 A (WATANABE et al) 16 February 1993, col. 4, lines 10-12.	20
Y,P	US 5,958,616 A (SALINAS et al) 28 September 1999, col. 3, lines 1-6.	13

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : H01M	A2	(11) International Publication Number: WO 00/45448 (43) International Publication Date: 3 August 2000 (03.08.00)
(21) International Application Number: PCT/US00/01810 (22) International Filing Date: 24 January 2000 (24.01.00) (30) Priority Data: 60/116,747 22 January 1999 (22.01.99) US (63) Related by Continuation (CON) or Continuation-in-Part (CIP) to Earlier Application US 60/116,747 (CIP) Filed on 22 January 1999 (22.01.99) (71) Applicant (for all designated States except US): CALIFORNIA INSTITUTE OF TECHNOLOGY [US/US]; 1200 East California Boulevard, Pasadena, CA 91125 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): NARAYANAN, S., R. [-/US]; - (US). ATTI, Tony [-/US]; - (US). PRAKASH, Surya [-/US]; - (US). OLAH, George [-/US]; - (US). SMART, Marshall, C. [-/US]; - (US). (74) Agent: HARRIS, Scott, C.; Fish & Richardson P.C., Suite 1400, 4225 Executive Square, La Jolla, CA 92037 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: IMPROVED MEMBRANE ELECTRODE ASSEMBLY FOR A FUEL CELL (57) Abstract A catalyst ink for a fuel cell including a catalytic material and poly(vinylidene fluoride). The ink may be applied to a substrate to form an electrode, or bonded with other electrode layers to form a membrane electrode assembly (MEA).		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Description

5

10

15

20

25

30

35

40

45

50

55

IMPROVED MEMBRANE ELECTRODE ASSEMBLY FOR A FUEL CELL

This application claims the benefit of provisional application U.S. Serial No. 60/116,747, filed January 22, 1999.

FIELD OF THE INVENTION

This invention relates to membrane electrode assemblies for direct feed methanol fuel cells. In particular, this invention relates to catalytic ink formulations for membrane electrode assemblies.

BACKGROUND

Many advanced direct methanol fuel cell systems use as the electrolyte a proton-exchange membrane made of perfluorocarbon material available from E.I. duPont, Wilmington, DE, USA, under the trade designation NAFION 117. However, when NAFION based membranes are used in direct methanol fuel cell applications, the methanol diffusion through the membranes is too high, which allows some fuel to cross over to the cathode side of the cell. Methanol crossover to the cathode results in fuel loss, lower overall efficiency and lower cell performance. Thus, a large amount of research has focused upon methods to decrease the methanol crossover rates in direct methanol fuel cells.

In addition to problems of methanol crossover, large water permeability is observed with NAFION based systems, which causes water management problems in fuel cell stacks. To address these issues, an alternative polymer electrolyte membrane has been proposed that is made of a composite of polystyrene sulfonic acid and poly(vinylidene difluoride). Initial studies of PSSA-PVDF membranes have shown lower methanol permeability than NAFION 117 membranes and comparable proton conductivity.

Conventional PSSA-PVDF membrane MEAs have been prepared using the same processes used to prepare NAFION membrane MEAs. Catalyst electrodes are prepared by making a catalyst ink including a catalyst material, typically either Pt or Pt/Ru, and an

5 alcohol solution of a perfluorosulfonic acid ionomer available from E.I. duPont de Nemours,
Wilmington, DE, USA under the trade designation Nafion-H. The catalyst ink was either
10 applied to a substrate such as porous carbon paper or, alternatively, directly deposited upon
the membrane surface. This sandwich structure was then placed in a hot press for bonding
5 with catalyzed TEFLON impregnated porous carbon electrodes to form a single MEA
component. While this method worked well for MEAs with NAFION membranes, MEA
15 samples made with the PSSA-PVDF membranes made by this process displayed
substantially lower electrical performance in experimental fuel cells and were generally
characterized by high cell resistance and low catalyst utilization values.

10 Therefore, the electrical performance of MEAs with PSSA-PVDF membranes
20 requires further improvement for implementation in power sources.

SUMMARY

25 In one aspect, the invention is a catalyst ink for a fuel cell including a catalytic
material and poly(vinylidene fluoride).

15 In another aspect, the invention is a process for making a catalyst ink for a fuel cell,
including mixing components including a catalytic material and poly(vinylidene fluoride).

30 The catalyst ink may be applied to a surface of a substrate to form an electrode for a
fuel cell assembly. The substrate may be a membrane or a backing.

20 The electrode with the deposited ink layer may be bonded with a membrane or
another electrode at a temperature greater than about 180 °C to form a membrane electrode
35 assembly (MEA).

The MEA with the deposited ink layer may be incorporated into a fuel cell stack.

40 The catalytic ink of the invention improves the interfacial bonding characteristics of
the deposited electrocatalytic layers with the proton conducting moieties of the membrane
25 structure, which improves the electrical performance and reduces the impedance compared to
MEAs made with conventional inks. The catalytic ink of the invention also reduce methanol
crossover when used in a fuel cell stack. MEAs made with the catalytic inks of the invention
45 demonstrate good electrical performance, excellent crossover characteristics, and unique
water management properties when evaluated at the cell level.

The details of one or more embodiments of the invention are set forth in the accompanying drawings and the description below. Other features, objects, and advantages of the invention will be apparent from the description and drawings, and from the claims.

DESCRIPTION OF DRAWINGS

FIG. 1 is schematic cross sectional view of a direct feed fuel cell.

FIG. 2 is a plot of cell voltage vs. current density that compares the performance of a conventional membrane electrode assembly to that of a membrane electrode assembly of the invention.

Like reference symbols in the various drawings indicate like elements.

DETAILED DESCRIPTION

FIG. 1 illustrates a liquid feed organic fuel cell having anode 110, cathode 120 and solid polymer proton-conducting cation-exchange electrolyte membrane 130, preferably made of a perfluorinated proton-exchange membrane material available from E.I. duPONT de Nemours, Wilmington, DE, USA, under the trade designation NAFION. NAFION is a co-polymer of tetrafluoroethylene and perfluorovinylether sulfonic acid. Other membrane materials can also be used.

Anode 110, cathode 120 and solid polymer electrolyte membrane 130 are bonded to form a single multi-layer composite structure, referred to herein as membrane-electrode assembly "MEA" 140.

A fuel pump 150 is provided for pumping an organic fuel and water solution into anode chamber 160. The organic fuel and water mixture is withdrawn through outlet port 170 into a methanol tank 190 and recirculated. Carbon dioxide formed in anode chamber 160 is vented through port 180 within the tank 190. An air compressor 1100 is provided to feed oxygen or air into a cathode chamber 1120. Carbon dioxide and water are removed through a port 1140 in the cathode chamber 1120.

Prior to use, anode chamber 160 is filled with the organic fuel and water mixture. Cathode chamber 1120 is filled with air or oxygen either at ambient pressure or in a pressurized state. During operation, the organic fuel in anode chamber 160 is circulated past anode 110. Oxygen or air is pumped into cathode chamber 1120 and circulated past cathode 120. When electrical load 1130 is connected between anode 110 and cathode 120, electro-

5 oxidation of the organic fuel occurs at anode 110 and electro-reduction of oxygen occurs at
cathode 120. The occurrence of different reactions at anode 110 and cathode 120 give rise to
10 a voltage difference between those two electrodes.

Electrons generated by electro-oxidation at anode 110 are conducted through external
5 load 1130 and are captured at cathode 120. Hydrogen ions or protons generated at anode 110
are transported directly across membrane electrolyte 130 to cathode 120. A flow of current is
15 sustained by a flow of ions through the cell and electrons through external load 1130.

The cathode 120 is a gas diffusion electrode in which unsupported or supported
platinum particles are bonded to one side of the membrane 130. In the process of the
10 invention, a catalytic composition, referred to herein as a catalyst ink, is applied to at least
20 one surface of the membrane 130 or to at least one surface of an electrode backing material.

The cathode 120 and the anode 110 are gas diffusion electrodes in which
electrocatalyst particles are bonded to at least one side of the membrane 130. To make the
25 cathode 120 and the anode 110, an electrocatalytic composition, referred to herein as a
15 catalyst ink, is applied to at least one surface of the membrane 130 or to at least one surface
of an electrode backing material.

For the cathode 120, the catalytic material may be in the form of fine metal powders
30 (unsupported), or dispersed on high surface area carbon (supported), and is preferably
unsupported platinum black, fuel cell grade, available from Johnson Matthey Inc., USA or
20 supported platinum materials available from E-Tek Inc., USA. The loading of the alloy
particles in the electrocatalyst layer is preferably in the range of about 0.5 mg/cm² to about
35 4.0 mg/cm². More efficient electro-oxidation is realized at higher loading levels.

The electrocatalyst in the anode 110 is formed from supported or unsupported
platinum-ruthenium particles. A bimetallic powder, having separate platinum particles and
40 25 separate ruthenium particles gives better results than platinum-ruthenium alloy. In a
preferred embodiment, the platinum and ruthenium compounds are uniformly mixed and
randomly spaced throughout the material, i.e., the material is homogeneous. This
homogeneous bimetallic powder is used as the anode catalyst material. The preferred ratio of
45 platinum to ruthenium can be between 60/40 and 40/60. The desired performance level is
30 believed to occur at 60% platinum, 40% ruthenium. Performance degrades slightly as the
catalyst becomes 100% platinum. Performance degrades more sharply as the catalyst

5 becomes 100% ruthenium. For platinum-ruthenium, the loading of the alloy particles in the electrocatalyst layer is preferably in the range of about 0.5 mg/cm² to about 4.0 mg/cm².

10 More efficient electro-oxidation is realized at higher loading levels.

5 The catalyst ink may also include an ionomer to improve ion conduction and provide improved fuel cell performance. Ionomer materials perfluorosulfonic acid, e.g. NAFION, alone or in combination with TEFLON. A preferred form for the ionomer is a liquid
15 copolymer of perfluorovinylether sulfonic acid and tetrafluoroethylene. To improve the performance of PSSA-PVDF membranes, PVDF is added to the catalyst ink, preferably in a powder form.

20 While not wishing to be bound by any theory, it is believed that the formation of the proton conducting channels at the interface of the PSSA-PVDF membrane and deposited catalyst layer is governed by inter-miscibility of the various polymers. Conventional catalyst inks included only NAFION ionomer. However, NAFION and PVDF-PSSA do not have
25 similar properties, and the entropy of mixing between these two polymers is not favorable.

15 Therefore, to improve the miscibility between the polymers in the catalyst ink and the membrane, it is important to add a compatible ionomeric material to the catalyst ink so that the deposited catalyst layer acquires properties similar to the membrane. PVDF having a low
30 intrinsic permeability to methanol will result in low crossover through the anode structure into the membrane.

20 In addition, since PSSA-PVDF membranes do not swell significantly in water, they do not have the desired plasticity when the membrane is bonded to the electrodes under hot
35 pressing conditions. The use of a high boiling solvent in the catalyst ink, such as, for example, N,N-dimethylacetamide (DMA), provides a plasticizing effect. The use of N,N-dimethylacetamide (DMA) and other solvents also prevents membrane dry-out during the
40 MEA fabrication process and thereby result in an MEA that has a lesser tendency to delaminate.

45 The catalyst ink is preferably applied directly on at least one side of a substrate such as the membrane 130 or on an electrode backing material to form a catalyst-coated electrode. Suitable backing materials include, for example, carbon fiber papers manufactured by Toray
30 Industries, Tokyo, Japan. These carbon papers are preferably "TEFLONized" to be about 5 wt% in TEFLON.

5

10

5

The application process includes spraying or otherwise painting the catalyst ink onto the substrate, with both the ink and the substrate at or substantially near room temperature. No high temperature treatment step is required to activate the hydrophobic particles in the catalyst ink solution. After drying on the substrate, the loading of the catalyst particles onto the substrate is preferably in the range of about 0.5 mg/cm² to about 4.0 mg/cm².

15

The application of the catalyst ink on to the membrane is significantly improved if the membrane surface is roughened prior to application of catalyst ink. Surface roughening provides additional anchoring sites for the catalyst and the polymer.

20

10

The membrane may be roughened by contacting the membrane surface with a commercial paper coated with fine abrasive. The abrasive should preferably have a grit size in the range of about 200 to about 400.

25

15

The abrasive material should be selected such that particles of the abrasive impregnated in the membrane are tolerated by the fuel cell. Abrasives that are preferred are silicon nitride, boron nitride, silicon carbide, silica and boron carbide. Abrasive using iron oxide or aluminum oxide should be avoided as these materials result contaminate the membrane with metal ions leading to increased resistance and this is undesirable.

30

Both sides of the membrane are roughened. The membrane is then held in a fixture and preferably allowed to dry before the catalyst ink is painted.

35

20

The anode 110, the membrane 130, and the cathode 120 may be assembled into the membrane electrode assembly 140. Once bonded together, the anode 110, cathode 120 and membrane 130 form a single composite layered structure. Preferably, the electrode and the membranes are first laid or stacked on a CP-grade 5 Mil (0.013 cm), 12-inch (30.5 cm) by 12-inch (30.5 cm) titanium foil to prevent acid from the membrane from leaching into the electrode.

40

25

Improving the melt-flow characteristics of the polymer membrane during the hot pressing process enhances the interfacial bonding. TGA analysis indicates that PSSA-PVDF systems are relatively stable to about 220 °C. In addition, conductivity measurements of membrane samples before and after being subjected to high temperature (up to about 200 °C) suggest that loss of sulfonic acid groups (conducting moieties) does not occur under these conditions. Both of these aspects suggest that temperatures higher than about 180 °C should

50

55

be employed to improve the melt-flow characteristics of membrane sample, thus improving the interfacial bonding characteristics of the MEA.

The invention will now be further described with reference to the following non-limiting example.

EXAMPLE

Prior to deposition of the catalyst ink, PSSA-PVDF membrane samples were dried and the surface scoured with 240 grade abrasive-coated paper to roughen the membrane surface for enhanced bonding characteristics.

The membrane sample was then sandwiched between two TEFLON (PTFE) blocks with a 2 inch (5 cm) x 2 inch (5 cm) window exposed. The membrane sample is then dried with a hand held blower for approximately 30 minutes or until the membrane surface is taut and dry.

Two different types of catalyst ink mixtures were prepared. The inks were applied to the membrane surface and to the surface of a TEFLONized backing paper available from Toray Industries, Tokyo, Japan. The backing paper was impregnated with about 5% by weight TEFLON.

The catalyst ink mixtures in Table 1 were applied to the eventual anode and cathode sides of the membrane. Sonication was used to ensure adequate mixing of the components.

TABLE 1

ANODE	CATHODE
140 mg Pt/Ru	180 mg Pt
400 mg H ₂ O	400 mg H ₂ O
720 mg NAFION (5 wt%)	720 mg NAFION (5 wt%)
400 mg DMA	

The catalyst ink mixtures in Table 2 were applied to the carbon papers. Sonication was used to ensure adequate mixing of the components.

TABLE 2

ANODE	CATHODE
140 mg Pt/Ru	180 mg Pt
400 mg H ₂ O	400 mg H ₂ O
720 mg NaFION (5 wt%)	720 mg NAFION (5 wt%)

The catalyst ink prepared for the membrane was applied to the membrane surface using a painting technique. A painting technique was also used to apply the catalyst ink onto the carbon paper. For the carbon paper, one coat was applied one day prior to the MEA fabrication and a second coat approximately one hour prior to fabrication.

To fabricate the MEA, the catalytic coated membrane was positioned between the two painted gas diffusion electrodes on the surface of an 8 inch (20 cm) x 8 inch (20 cm) die. Once the membrane is positioned and fastened down, a fine coating of DMA/H₂O solution was painted on the membrane edges. A titanium plate was inserted on the top of the membrane and a copious amount (5-7 ml) of water was added to the die. The top plate was then inserted and the die was then placed into a hot press.

Once the die was inserted into the press the die platen was closed with a force of 2000-2500 lbs (909.1-1136 kg) over a 36 cm² area electrode. The die was heated to a temperature of 180-185 °C for a period of 15 minutes and then cooled using an automated chiller. Following this procedure, the die was opened and the MEA removed and assembled into a cell for evaluation.

The electrical performance of fuel cells employing membrane-electrode assemblies prepared by the process of the invention was measured and their performance compared with MEAs prepared by conventional processes. These results are shown in Figure 2 for 1.0 M MeOH and 20 psig O₂. Curve I shows fuel cell performance using an MEAs prepared by the process of the invention, while curve II represents an otherwise identical fuel cell using an MEA prepared by a conventional process.

The results demonstrate that the process of the invention leads to a higher fuel cell performance. Comparing curve I and curve II, the voltage at 150 mA/cm² is increased by about 0.1 V, and the improvement at higher current densities is more than 0.2 V.

5

10

5

15

20

25

30

35

40

45

50

55

The conditions of testing, for the results shown in Figure 2, were similar except for the temperature. It is important to remember that increasingly higher temperatures leads to improved performance in methanol fuel cells. The results show that even at a test temperature of 60 °C (curve I), the MEAs prepared by the process of the invention exceed the performance at 83 °C (curve II) obtained with MEAs prepared by the conventional process. Thus these results confirm the value of the process of the invention.

A number of embodiments of the invention have been described. Nevertheless, it will be understood that various modifications may be made without departing from the spirit and scope of the invention. Accordingly, other embodiments are within the scope of the following claims.

Claims

5

10

15

20

25

30

35

40

45

50

55

5

WHAT IS CLAIMED IS:

10

1 1. A catalyst ink for a fuel cell comprising a catalytic material and
2 poly(vinylidene fluoride).
3

15

1 2. The catalyst ink of claim 1, wherein the catalytic material comprises Pt.
2

1 3. The catalyst ink of claim 1, wherein the catalytic material comprises Pt and
2 Ru.
3

20

1 4. The catalyst ink of claim 1, further comprising a second ionomer.
2

25

1 5. The catalyst ink of claim 5, wherein the ionomer comprises a liquid
2 copolymer of tetrafluoroethylene and perfluorovinylethersulfonic acid.
3

30

1 6. A process for making a catalyst ink for a fuel cell, comprising mixing
2 components comprising a catalytic material and poly(vinylidene fluoride).
3

1 7. The process of claim 6, further comprising adding to the mixture a membrane
2 plasticizer.
3

35

1 8. The process of claim 7, wherein the plasticizer is a high boiling solvent.
2

1 9. The process of claim 7, wherein the plasticizer is N,N dimethylacetamide.
2

40

1 10. The process of claim 6, further comprising adding to the mixture a second
2 ionomer comprising a liquid copolymer of tetrafluoroethylene and
3 perfluorovinylethersulfonic acid.
4

45

1 11. A process for making an electrode for a fuel cell, comprising:
2

2 (a) providing a catalyst ink comprising a catalytic material and poly(vinylidene
3 fluoride); and

50

55

5

4 (b) applying the catalyst ink to at least one side of a substrate.

5

10

1 12. The process of claim 11, wherein the substrate is a membrane.

2

1 13. The process of claim 12, wherein the membrane is a PSSA-PVDF membrane.

2

15

1 14. The process of claim 11, wherein the ink further comprises a plasticizer.

2

1 15. The process of claim 14, wherein the plasticizer is N,N dimethylacetamide.

2

20

1 16. The process of claim 12, further comprising roughening the surface of the
2 membrane prior to applying the catalyst ink.

3

25

1 17. The process of claim 12, wherein the substrate is a backing.

2

1 18. The process of claim 17, wherein the backing is a carbon paper.

2

30

1 19. A process for making a membrane electrode assembly for a fuel cell,
2 comprising:

3 (a) providing a catalyst ink comprising a catalytic material and poly(vinylidene
4 fluoride);

35

5 (b) applying the catalyst ink to at least one side of a membrane; and

6 (c) bonding the membrane to at least one electrode.

7

40

1 20. The process of claim 19, wherein the membrane is bonded to the electrode at a
2 temperature of greater than about 180 °C.

3

1 21. The process of claim 19, wherein the catalyst ink further comprises a
2 plasticizer.

45

3

1 22. The process of claim 21, wherein the plasticizer is N,N dimethylacetamide.

50

55

5

2

10

1 23. The process of claim 19, further comprising adding to the catalyst ink a
2 second ionomer comprising a liquid copolymer of tetrafluoroethylene and
3 perfluorovinylethersulfonic acid.

4

15

1 24. The process of claim 19, further comprising roughening the surface of the
2 membrane prior to applying the catalyst ink.

3

20

1 25. The process of claim 19, wherein the electrode comprises a catalyst layer
2 comprising a catalytic material selected from Pt and Pt/Ru and an ionomer.

3

25

1 26. A fuel cell comprising a membrane electrode assembly, wherein the
2 membrane electrode assembly is made by the process of:

3 (a) providing a catalyst ink comprising a catalytic material and poly(vinylidene
4 fluoride);

5 (b) applying the catalyst ink to at least one side of a membrane; and

6 (c) bonding the membrane to at least one electrode.

30

7


35

40

45

50

55





**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.